



## KER<sup>®</sup> 1507

### Emulsion Styrene-Butadiene Rubber (E-SBR)

#### CHARACTERISTICS

KER<sup>®</sup> 1507 is a standard emulsion styrene-butadiene rubber. It is produced by cold emulsion copolymerization technology based on soaps of rosin and fatty acids and contains 23.5% chemically bonded styrene. It is coagulated by a system of acid and synthetic coagulant, does not contain extender oil and is stabilized by a non-staining antioxidant.

KER<sup>®</sup> 1507 is also available as bio/circular attributed E-SBR under ISCC Plus certification.

#### CHEMICAL AND PHYSICAL DATA

PROPERTY	TEST METHOD	UNIT	VALUE
Mooney viscosity <sup>(1)</sup>	ASTM D1646	MU	36 ÷ 42
Volatile matter	ASTM D5668	% wt.	max 0,7
Total Ash	ASTM D5667	% wt.	max 0,4
Organic acids	ASTM D5774	% wt.	5 ÷ 7,5
Soaps	ASTM D5774	% wt.	max 0,4
Bounded styrene	ASTM D5775	% wt.	22 ÷ 25

(1) ML 1+4 (100°C) massed sample

#### APPLICATION

KER<sup>®</sup> 1507 is suitable for the production of tires, rubber compounds for the footwear industry and for the production of molded, calendered and colored articles with light shades. It is approved for the production of rubber goods that come into contact with food or drinking water.

#### PACKAGING

- KER<sup>®</sup> 1507 is supplied in bales with a nominal weight of 33 kg (± 0,5 kg).
- Each bale is wrapped in PE foil which is integral part of the product.
- One returnable metal box contains 36 bales (nominal 1188 kg).

#### TRANSPORTATION AND STORAGE

KER<sup>®</sup> 1507 is generally shipped in covered trucks, covered rail cars and standard shipping containers and is not a hazardous material. KER<sup>®</sup> 1507 should be stored in sheltered conditions away from direct sun light, an adequately ventilated area and at least 2 meters away from radiant heating elements where it should not exceed temperatures above 30°C. Under these conditions KER<sup>®</sup> 1507 has a shelf life of at least 12 months.

None of the companies belonging to Synthos Group (Synthos) make warranties, either express or implied, in this document; all implied warranties of merchantability or fitness for a particular purpose are expressly excluded. Since the conditions and methods of use of the information and products referred to are beyond Synthos's knowledge and control, Synthos disclaims any and all liability for losses or damages that may result from reliance on the information or use of the products described herein. Synthos makes no warranties, express or implied, that the use of any Synthos product will be free from any infringement claims.

Date of edition:

01/04/2023

[synthosgroup.com](http://synthosgroup.com)

