

MIKROFINE® ADC-F1/F3

MIKROFINE® ADC-F1/F3 is a universally employed chemical blowing agent in powder form for the production of cellular plastics. MIKROFINE® ADC-F1/F3 is available with a very close distribution in self-dispersible and activated grades.

1 PRODUCT INFORMATION

Main Constituent	:	Azodicarbonamide CAS Number [123-77-3] Mol. Formula C ₂ H ₄ N ₄ O ₂ Mol.wt. 116
Physical form	:	Pale yellow free flowing powder
Odour	:	Odourless
Solubility	:	Insoluble in water and benzene. Soluble in dimethylformamide.
Health, safety & handling information	:	Relevant information can be found in sheet No. HPLA/MSDS/M/CBA/01

2 SPECIFIED PROPERTIES

Decomposition temperature (°C) (open capillary tube method)	:	
ADC F1	:	200 ± 3
ADC F3	:	191 ± 2
Gas content (ml/gm at STP)	:	
ADC F1	:	235 ± 5
ADC F3	:	230 ± 5
Volatility (% w/w)	:	0.5 max
pH (5% aqueous suspension at 25°C)	:	7.3 ± 0.5
Average particle diameter (micron)	:	3.5-4.5

3 SPECIAL FEATURES

MIKROFINE[®] ADC-F1/F3 is completely dispersible. The products have a narrow particle size distribution for reliable performance.

MIKROFINE[®] ADC-F1/F3 has been specially developed to produce white foams in PVC plastisol applications where it can be incorporated into PVC-plastisol as a dry powder during the normal mixing cycle. A pre-dispersion in a plasticizer is not needed.

Setting problems experienced with most blowing agent - plasticizer dispersions are eliminated with MIKROFINE[®] ADC-F1/F3 grades.

MIKROFINE[®] ADC-F1/F3 products are free flowing powders which do not agglomerate. This makes these products ideal for metering in hopper blender units on extruders and injection moulding machines.

MIKROFINE[®] ADC-F1/F3 products can be incorporated into rubber compounds at the end of the mixing process and disperses easily in all compounds (even with relatively low viscosity).

With MIKROFINE[®] ADC-F1/F3 products vulcanizates with fine, uniform cell structure and smooth surface can be obtained and these products do not impart discolouration or odour to vulcanizates.

4 APPLICATIONS

MIKROFINE[®] ADC-F1/F3 is used in a wide variety of polymers for the production of foamed articles based on plasticized or unplasticized PVC, HDPE/LDPE, EVA co-polymers, natural & synthetic rubber, Polypropylene & ABS. It is specially suitable for PVC plastisol application where it produces whiter foams with uniform & fine cell structure.

MIKROFINE[®] ADC-F1/F3 is a blowing agent for rubber compounds where it can be easily incorporated at the end of mixing process and results in even dispersion. With MIKROFINE[®] ADC-F1/F3 vulcanizates with extremely fine uniform cell structure free from any discoloration or odour, can be obtained. Wall papers, artificial leather cloth, floor and wall coverings, thermo insulating materials, insulating sealant, carpet backing, cellular ceramic, door sealing strips, profiles, sheets, foot wear midsoles /insoles and automotive components are some of the application areas.

5 DOSAGE

0.5 - 6.0 PHR depending on the polymer used and the extent of expansion required.

6 PACKING

MIKROFINE[®] ADC-F1/F3 grades are packed in 25kg HDPE bags/ 20kg or 25kg UN approved corrugated cartons with a polythene liner inside or as per customer's requirement.

The information given in this document is only a recommendation, believed to be reliable and is given in good faith but without warranty. Our advice does not release users from the obligation of checking its validity. The user should test the product to ascertain the suitability for the intended use. Specified properties mentioned in this document are based on our historical production performance and these properties or the whole document is subject to change without any prior notice, at our sole discretion. We are under no obligation to recall earlier issued documents.

HPL Additives Limited

803, Vishal Bhawan, 95 Nehru Place
New Delhi - 110 019, INDIA.

Tel. : +91-11-2643 1522, 2642 1570

Fax : +91-11-2647 4350, 2646 0981

e-mail : hpll@hpl-group.com