



Silquest* A-1170

Silquest* A-1170

Description

Silquest A-1170, Silquest Y-9627 and Silquest Y-11699 silanes are secondary aminofunctional bis-silanes. This category of silanes is generally useful to consider for a broad range of applications to promote adhesion in coatings, adhesives and sealants between organic polymers and glass, metal, wood or cast plastic substrates.

Typically, they can function as coupling agents to particulate mineral fillers in composites, as in foundry molds and cores, to improve mechanical properties such as tensile and flexural strengths.

These property improvements have been maintained in the presence of aggressive environments, such as high temperature and high humidity conditions.

Key Features and Benefits

- Bis-silyl functionality - generally affords greater bonding or adhesion promotion to inorganic substrates.
- Secondary amino functionality - can typically improve shelf stability in various resin systems.
- Methoxy silane ester versions Silquest A-1170 silane and Silquest Y-9627 silane generally offer fast reaction with moisture, which translates to rapid cure or adhesion build.
- Ethoxy silane ester version Silquest Y-11699 silane generally provides a controlled cure with a by-product of the coupling or crosslinking mechanisms that have a lower impact on the environment.

Typical Physical Properties

Property	Silquest A-1170 silane	Silquest Y-9627 silane	Property	Silquest Y-11699
Appearance	Clear liquid	Clear liquid	Appearance	Clear liquid
Color	Clear, pale	Straw to dark	Color	Pale
Odor	Ester	Ester	Odor	Ester
Percent Actives	100	100	Percent Actives	100
Density, g/cm ³	1.04	1.03	Density, g/cm ³	0.968
Percent Purity	> 95 / 90	> 95 / 90	Flash Point, Estimated,ASTM D93, °C (°F)	> 93 (200)
Specific Gravity, 25/25°C	1.0423	1.0423	Boiling Point, °C	>150
Flash Point, PMCC, ASTM Method D 93, °C (°F)	112.7 (235)	82 (179.6)	Freezing Point, °C (°F)	< 0 (32)
Boiling Point, at 4mm Hg, °C (°F)	152 (306)	>100 (>212)	Molecular Weight, g/mole	425.5
Molecular Weight, g/mole	341.5	341.5		

*Silquest is a trademark of Momentive Performance Materials Inc.

Potential Applications

Amino bis-silanes such as Silquest A-1170, Silquest Y-9627 and Silquest Y-11699 silanes have been shown to be effective in reacting with epoxy, urethane, melamine, polyimide, phenolic and furan thermosetting resins as well as many thermoplastics, such as polyamides and polyesters.

Silquest* A-1170

Durable water-resistant bonds are generally achieved when the silyl portion of these aminosilanes are condensed with an inorganic surface and are covalently bonded with the resin matrix of the composite, paint, adhesive or sealant.

The bis-alkoxysilane structure of the Silquest A-1170, Silquest Y-9627 and Silquest Y-11699 silanes result in the addition of two silyl groups to a resin. This typically yields more durable wet adhesion and more efficient bonding per mole of added silane.

The ethoxy ester groups, as on Silquest Y-11699 silane, generally provide slower reaction with moisture, giving longer shelf stability when exposed to incidental or atmospheric moisture on storage.

The Silquest A-1170 silane and Silquest Y-9627 silane, as the methoxy ester versions, generally offer a quick cure and or rapid adhesion build.

The higher purity grade of Silquest A-1170 silane may be considered for applications which demand low color, and greater control of reaction stoichiometry.

Silquest Y-9627 silane may be considered for similar reactivity with potential savings.

These versatile silanes typically can be added directly to polymers during system formulation, or used independently as primers.

Typical Sealant Application – Adhesion to Cast Plastics

The Effect of Silquest A-1170 / Silquest Y-9627 Silanes on Adhesion of Filled RTV Silicone to Plastic Substrates

Substrate	Adhesion, pli w/ Silquest A-1170 or Silquest Y-9627 Silanes		Control	
	Wet	Dry	Wet	Dry
ABS	17	24	0.1	0.1
PVC	29	32	1.3	0.5
Styrene	31	31	1.1	0.5
Acrylic	26	36	0.5	0.5

Note: Test data. Actual results may vary.

Typical Foundry – Sand Mold Compounds

FURAN			PHENOLIC		
		Parts By Weight			Parts By Weight
Furfuryl Alcohol/ Phenol Resin		2.0	Resin		1.0
Silica Foundry Sand		100.0	Silica Foundry Sand		100.0
Silquest A-1170 / Silquest Y-9627 Silanes		0.10	Silquest A-1170 / Silquest Y-9627 Silanes		0.1
Hardener		0.60	Benzene Sulfonic Acid		0.4
Measured Properties			Measured Properties		
	No Silane	Silane		No Silane	Silane
Flexural Strength, Initial (psi)	142	187	Tensile Strength, Initial	11.0	53.0
Flexural Strength, Aged in resin -2 months	77	130	Tensile Strength, Aged in 2 months	16.0	69.0

Product formulations are included as illustrative examples only. Momentive makes no representation or warranty of any kind with respect to any such formulations, including, without limitation, concerning the efficacy or safety of any product manufactured using such formulations.

*Silquest is a trademark of Momentive Performance Materials Inc.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at www.momentive.com or, upon request, from any Momentive Performance Materials (MPM) representative. **For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center.** Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

For product prices, availability, or order placement, contact our customer service by visiting momentive.com/ContactSilicones.

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER

The information provided herein was believed by Momentive Performance Materials Inc. (collectively with its subsidiaries, "Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for user's intended application or use. All products supplied by Momentive are subject to Momentive's standard terms and conditions of sale. **MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE**, except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any product.

*Silquest is a trademark of Momentive Performance Materials Inc.

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.